

A-BASALT

The Painted Metal Atelier

A-BASALT

The application of our many years of know-how in the world of pre-painted metals allows us to best satisfy the creative needs of **architecture** and **design** projects.

A-Basalt is a product in our **Premium Collection** inspired by Dolomite mountains.

These rocks represent an aesthetic in which essentiality and functionality achieve a perfect equilibrium.

Simultaneously condensing beauty and power, the Dolomites (UNESCO World Heritage Site) express a "harmonic chromatic contrast" between pale limestone and dark volcanic basaltic rocks.

Thanks to **A-Basalt**, our **pre-painted metal Atelier** is able to reproduce the beauty of these **great rock walls** to best satisfy every design requirement.



A-BASALT

A-Basalt is the result of a pre-painting production process involving the application of polyester paints on aluminium support materials to achieve a finished appearance similar to **stone**.

This finish is applicable to the most varied uses, both **outdoors**, and for **interior** settings.

A-Basalt is suitable for **covers** and **roofing**, when protection is required from outdoor agents (sun, rain, dust, etc.) and when you want to bring extra aesthetic impact to an entire building.

"False stone" is one of the most recent trends in interior design because it gives settings a touch of rustic and natural charm, while also fitting perfectly into the most modern interiors where it provides striking elements of contrast.





TREATMENT

2 degreasings + chrome-free passivation

TOP SURFACE

BASE: 14 - 16 microns INK: 1 - 2 microns TOP TRASPARENT: 14 - 16 microns

BACK SURFACE BACK COAT: 5 - 7 microns

UV Radiation Resistance Category: RUV3 Coating used: compliant with **RoHS** Directive

Technical Features

TEST	VALUE	REFERENCE STANDARD
Thickness	50±10μm**	EN 13523-1 (ECCA T1)
Gloss	5 ± 3	EN 13523-2 (ECCA T2)
Pencil hardness	F-H	EN 13523-4 (ECCA T4)
Adhesion on impact	100%	EN 13523-5 (ECCA T5)
Adhesion on forming	100%	EN 13523-6 (ECCA T6)
T.B. Adherence at 25° C	OT - 1T*	EN 13523-7 (ECCA T7)
T.B. Cracking at 25° C	OT - 2,5T*	EN 13523-7 (ECCA T7)
MEK	> 100	EN 13523-11 (ECCA T11)

^{*} according to the characteristics of the support



our applications



min. 500 mm · max. 1.320 mm min. 0.3 mm · max. 1.5 mm External coil diameter min. 700 mm · max. 1,300 mm Internal coil diameter 508 mm: 610 mm min. 20 mm Strip width





^{**} the measured thickness (DFT) is apparent

Alusteel Coating

via Risorgimento, 19 26867 Somaglia, Lodi, Italy T +39 0377 579700 info@alusteel.it www.alusteel.it

Alpine Anodizing

via Friuli, 75 24055 Cologno al Serio, Bergamo, Italy T +39 035 897128 info@alpineanodizing.it www.alpineanodizing.it

Metalcoat

via Antonio Stoppani, 10/C 24121 Bergamo, Italy T+39 035 246509 info@metalcoat.it www.metalcoat.it

Aleu - Aluminium Europe

piazza Francesco Buffoni, 5 21013 Gallarate, Varese, Italy T+39 0331 1420010 info@aleu.it www.aleu.it

